

# Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/000697

International filing date: 10 January 2005 (10.01.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US  
Number: 10/758,678  
Filing date: 15 January 2004 (15.01.2004)

Date of receipt at the International Bureau: 18 February 2005 (18.02.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland  
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

17698 U.S. PTO  
011504

Please type a plus (+) sign in this box ☐ ☒  
Approved for use through 10/31/2002. OMB 0851-0032  
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE  
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**UTILITY  
PATENT APPLICATION  
TRANSMITTAL**

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Attorney Docket No.	80002/US01
First Inventor	Parker et al.
Title	PROCESS FOR PRODUCTION OF A CARBOXYLIC ACID/DIOL MIXTURE SUITABLE FOR USE IN POLYESTER PRODUCTION
Express Mail Label No.	ER786767122US

15757 U.S. PTO  
10758678  
011504

APPLICATION ELEMENTS <i>See MPEP chapter 600 concerning utility patent application contents.</i>	ADDRESS TO: Commissioner for Patents Mail Stop Patent Application P.O. Box 1450 Alexandria, VA 22313-1450
1. <input checked="" type="checkbox"/> Specification (Total Pages 38 )	5. <input type="checkbox"/> Assignment Papers (cover sheet & documents(s))
2. <input checked="" type="checkbox"/> Drawing(s) (35 USC 113) (Total Sheets 2 )	6. <input checked="" type="checkbox"/> Information Disclosure Statement (IDS) <input checked="" type="checkbox"/> Copies of IDS Citations <input type="checkbox"/> Copy of IDS from Prior Application
3. Oath or Declaration (Total Pages 3 )	7. <input type="checkbox"/> Preliminary Amendment
a. <input checked="" type="checkbox"/> Newly executed (original or copy)	8. <input checked="" type="checkbox"/> Return Receipt Postcard (MPEP 503) (Should be specifically itemized)
b. <input type="checkbox"/> Copy from a prior application (37CFR 1.63(d)) (for continuation/divisional with Box 12 completed)	9. <input type="checkbox"/> Certified Copy of Priority Document(s) (if foreign priority is claimed)
i. <input type="checkbox"/> DELETION OF INVENTOR(S) Signed statement attached deleting inventor(s) named in the prior application, see 37CFR 1.63(d)(2) and 1.33(b).	10. <input type="checkbox"/> Nonpublication Request under 35 U.S.C. 122 (b)(2)(B)(i). Applicant must attach form PTO/SB/35 or its equivalent.
4. <input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76	11. <input type="checkbox"/> Other: _____

12. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment, or in an Application Data Sheet under 37 CFR 1.76:

<input type="checkbox"/> Continuation	<input type="checkbox"/> Divisional	<input type="checkbox"/> Continuation-in-part (CIP)	of prior application No.: _____
Prior application Information: Examiner _____			Group/Art Unit: _____

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure to the prior application, from which an oath or declaration is supplied under Box 3b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

CLAIMS	(1) FOR	(2) NUMBER FILED	(3) NUMBER EXTRA	(4) RATE	(5) CALCULATIONS
TOTAL CLAIMS (37 CFR 1.16(c))		60 - 20 =	40	X \$18 =	720
INDEPENDENT CLAIMS (37 CFR 1.16(b))		9 - 3 =	6	X \$86 =	516
MULTIPLE DEPENDENT CLAIMS (if applicable) (37 CFR 1.16(d))				+ \$290 =	290
				BASIC FEE (37 CFR 1.18(a))	770
				TOTAL to be CHARGED =	\$2,296

The Commissioner is hereby authorized to charge any additional fees under 37 CFR 1.16 and 1.17 which may be required by this paper or credit any overpayment to Deposit Account No. 05-0221. Any submission during prosecution which requires an EOT should be treated as including a Petition for the required extension and be charged to Deposit Account No. 05-0221. A duplicate copy of this sheet is enclosed.

**13. CORRESPONDENCE ADDRESS**

NAME Steven A. Owen	SIGNATURE <i>Steven A. Owen</i>	DATE 1/15/2003
ADDRESS Eastman Chemical Company P.O. Box 511 Kingsport, Tennessee 37662-5075	REGISTRATION NUMBER: 50,355 PHONE: (423) 229-5534 FAX: (423) 229-1239	EMAIL: sowen@eastman.com

**CERTIFICATE OF MAILING UNDER 37 CFR 1.10**

"EXPRESS MAIL" Mailing Label No.: ER786767122US Date of Deposit: 1/15/04

I hereby certify that this Utility Patent Transmittal and the Documents referred to as being enclosed therein are being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to Mail Stop Patent Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

*Kristi D. Huff*  
Kristi D. Huff

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, Mail Stop Patent Application, P.O. Box 1450, Alexandria, VA 22313-1450.

## **PROCESS FOR PRODUCTION OF A CARBOXYLIC ACID/DIOL MIXTURE SUITABLE FOR USE IN POLYESTER PRODUCTION**

5

### **FIELD OF INVENTION**


The present invention relates to a process by which a carboxylic acid/diol mixture is obtained from a slurry or cake carboxylic acid product without isolation of a substantially dry carboxylic acid solid. More specifically, the present invention relates to a process by which a terephthalic acid/diol mixture suitable as a starting material for polyester or co-polyester production is obtained from a slurry or cake terephthalic acid product without isolation of a substantially dry terephthalic acid solid.

15

### **BACKGROUND OF THE INVENTION**

Pursuant to the goal of making polyethylene terephthalate (PET) and other polyesters or co-polyesters, a great deal of patent literature is dedicated to describing the processes for preparing a carboxylic acid/diol mixture suitable as starting material. In general, these inventions describe specific mixing schemes with a purified terephthalic acid solid and liquid ethylene glycol. Additionally, there is substantial body of literature devoted to describing the production of a purified terephthalic acid in powder form that is suitable for use in producing PET and other polyesters or co-polyesters.

1284171



# THE UNITED STATES OF AMERICA

**TO ALL TO WHOM THESE PRESENTS SHALL COME:**

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

*February 10, 2005*

**THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.**

**APPLICATION NUMBER: 10/758,678  
FILING DATE: January 15, 2004  
RELATED PCT APPLICATION NUMBER: PCT/US05/00697**



Certified by

Under Secretary of Commerce  
for Intellectual Property  
and Director of the United States  
Patent and Trademark Office

The objective of this invention is to describe a process by which the carboxylic acid/diol mixture suitable as a starting material for polyester or co-polyester production is obtained from a slurry or cake carboxylic acid product without isolation of a substantially dry carboxylic acid solid. More specifically, the objective of this invention is to describe a process by which a terephthalic acid/diol mixture suitable as a starting material for polyester or co-polyester production is obtained from a slurry or cake terephthalic acid product without isolation of a substantially dry terephthalic acid solid.

Usually, purified terephthalic acid solid is produced in a multi-step process wherein a crude terephthalic acid is produced. Liquid phase oxidation of p-xylene produces crude terephthalic acid. The crude terephthalic acid does not have sufficient quality for direct use as starting material in commercial PET. Instead, the crude terephthalic acid is usually refined to purified terephthalic acid solid.

Usually, in terephthalic acid purification processes, the crude terephthalic acid is dissolved in water and hydrogenated for the purpose of converting 4-carboxybenzaldehyde to p-toluic acid, which is a more water-soluble derivative, and for the purpose of converting characteristically yellow compounds to colorless derivatives. Significant 4-carboxybenzaldehyde or p-toluic acid in the final purified terephthalic acid product is particularly detrimental to polymerization processes as each can act as a chain terminator during the condensation reaction between

terephthalic acid and ethylene glycol in the production of PET. Typical purified terephthalic acid contains on a weight basis less than 25 parts per million (ppm) 4-carboxybenzaldehyde and less than 150 ppm p-toluic acid.

A number of other processes have been developed where a  
5 terephthalic acid suitable as starting material for commercial PET production is produced without the use of hydrogenation. Typically, terephthalic acid production processes usually involve catalyzed oxidation of p-xylene in an acetic acid solvent followed by filtration and drying of the terephthalic acid.

10 To produce a terephthalic acid/diol mixture acceptable for PET production from a slurry or cake terephthalic acid product poses a substantially different problem than from a dry terephthalic acid powder.

Typically, terephthalic acid (TPA) produced via catalyzed oxidation of p-xylene in an acetic acid solvent produces a slurry or cake terephthalic  
15 acid product that contains residual catalyst (e.g cobalt, manganese, and bromine compounds). In a common method of producing a substantially dry TPA solid from a slurry or cake terephthalic acid product, the slurry or cake terephthalic acid product is filtered to separate a substantial amount of the acetic acid liquid from the TPA solids. Residual catalyst is usually  
20 separated from the slurry or cake terephthalic acid product by washing

(rinsing) the wet cake with catalyst-free acetic acid, water or other solvent. The TPA solid is isolated by drying.

In the present invention, a novel process has been discovered resulting in fewer steps than the currently employed processes. The primary utility of the invention is reduction of capital and operating costs associated with the isolation and drying of a terephthalic acid powder. In the conventional approach toward producing terephthalic acid via catalyzed oxidation of p-xylene in an acetic acid solvent, a slurry or cake terephthalic acid product is filtered, washed, then dried to produce a terephthalic acid powder suitable as starting material for PET production.

In one embodiment of the present invention, the slurry or cake terephthalic acid product is filtered to produce a terephthalic acid cake with solvent and a solvent mother liquor stream. The terephthalic acid cake with solvent is then washed (rinsed) with water to recover residual metal catalyst material and to produce a water-wet terephthalic acid cake and a solvent/water by-product liquor. The water-wet terephthalic acid cake is then combined with a diol to produce a terephthalic acid/diol mixture suitable as starting material in a commercial PET process. By eliminating conventional processes for isolating and drying a terephthalic acid solid, the equipment and energy necessary to produce a terephthalic acid powder is also eliminated.

Another surprising and seemingly contradictory aspect of the invention is the benefit of addition of water to the acetic acid and ethylene glycol solvents. In general, in conventional processes for producing terephthalic acid, it is necessary to remove water produced in the oxidation  
5 process. Typically, use of acetic acid as an oxidation solvent necessitates an additional process step where acetic acid and water are separated. It is seemingly contradictory to produce an acetic acid and water mixture when it can be avoided by drying the terephthalic acid from the acetic acid solvent.

Additionally, in processes for producing PET via esterification of TPA  
10 with ethylene glycol, water is generated as a reaction by-product. In general, it is necessary to remove the water produced in the esterification process via an additional process step where ethylene glycol and water are separated. It is seemingly contradictory to produce an ethylene glycol and water mixture when it can be avoided by not introducing water with the  
15 TPA. However, a benefit of this invention is based on the premise that ethylene glycol/water and acetic acid/water separation systems normally exist for conventional TPA and PET production processes. In this invention, the value associated with eliminating the TPA drying can be of great benefit when compared to traditional TPA production processes.



## SUMMARY OF THE INVENTION

The present invention relates to a process by which a carboxylic  
5 acid/diol mixture is obtained from a slurry or cake carboxylic acid product  
without isolation of a substantially dry carboxylic acid solid. More  
specifically, the present invention relates to a process for the production of  
a terephthalic acid/ethylene glycol mixture suitable as feedstock for the  
production of commercial PET. The resulting process can save energy and  
10 has fewer steps than currently employed processes. Specifically, the  
present invention incorporates a direct displacement of water with ethylene  
glycol. Incorporation of the displacement step eliminates the need to isolate  
a purified terephthalic acid solid and could eliminate the need for  
crystallization, solid-liquid separation, drying and solids handling equipment  
15 normally found in commercial purified terephthalic acid processes.

It is an object of this invention to provide a process for producing a  
carboxylic acid/diol mixture from a slurry or cake carboxylic acid product  
without isolation of a substantially dry carboxylic acid solid.

It is an object of this invention to provide a process for producing a  
20 carboxylic acid/diol mixture from a slurry or cake carboxylic acid product  
suitable as starting material for the production of polyesters or co-polyesters  
without isolation of a substantially dry carboxylic acid solid.

It is another object of this invention to provide a process for producing a terephthalic acid/diol mixture from a slurry or cake terephthalic acid product without isolation of a substantially dry terephthalic acid solid.

It is another object of this invention to provide a process for  
5 producing a terephthalic acid/ethylene glycol mixture from a terephthalic acid solvent slurry or cake without isolation of a substantially dry terephthalic acid solid.

It is another object of this invention to provide a process for producing a terephthalic acid/ethylene glycol mixture without isolation of a  
10 substantially dry terephthalic acid solid by removing water from a water-wet terephthalic acid cake through the use of a carboxylic acid/diol mixing zone.

In a first embodiment of this invention, a process for producing a carboxylic acid/diol mixture is provided, the process comprises:

- (a) removing in a liquor exchange zone impurities from a  
15 carboxylic acid slurry to form a water-wet carboxylic acid cake, a mother liquor stream, a solvent mother liquor stream, and a solvent/water byproduct liquor stream;
- (b) routing the water-wet carboxylic acid cake to a vapor seal zone; and
- 20 (c) adding at least one diol to the water-wet carboxylic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to form the carboxylic acid/diol mixture.

In another embodiment of this invention, a process for producing a carboxylic acid/diol mixture is provided, the process comprises:

- 5 (a) removing in a solvent liquor exchange zone impurities from a carboxylic acid slurry to form a carboxylic acid cake with solvent, a mother liquor stream, and a solvent mother liquor stream;
- (b) adding water in a water wash zone to the carboxylic cake with solvent to produce a water-wet carboxylic acid cake and a solvent/water byproduct liquor stream;
- (c) routing the water-wet carboxylic acid cake to a vapor seal  
10 zone; and
- (d) adding at least one diol to the water-wet carboxylic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to form the carboxylic acid/diol mixture.

In another embodiment of this invention, a process for producing a  
15 carboxylic acid/diol mixture is provided, the process comprises:

- (a) removing in a solid-liquid separation zone impurities from a carboxylic acid slurry to form a slurry or cake carboxylic acid product and a mother liquor stream;
- (b) removing in a solvent-water liquor exchange zone impurities  
20 from the slurry or cake carboxylic acid product to form a water-wet carboxylic acid cake, a solvent mother liquor stream, and a solvent/water byproduct liquor stream;

(c) routing the water-wet carboxylic acid cake to a vapor seal zone; and

(d) adding at least one diol to the water-wet carboxylic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to  
5 form the carboxylic acid/diol mixture.

In another embodiment of this invention, a process for producing a carboxylic acid/diol mixture is provided, the process comprises:

(a) removing a solvent from a slurry or cake carboxylic acid product in a solvent-water liquor exchange zone; wherein a substantial  
10 portion of the solvent in the slurry or cake carboxylic acid product is replaced with water to form a water-wet carboxylic acid cake;

(b) routing the water-wet carboxylic acid cake to a vapor seal zone; and

(c) adding at least one diol to the water-wet carboxylic acid cake  
15 in a carboxylic acid/diol mixing zone to remove a portion of the water to form the carboxylic acid/diol mixture.

In another embodiment of this invention, a process for producing a terephthalic acid/diol mixture is provided, the process comprises:

(a) removing in a solvent wash zone impurities from a slurry or  
20 cake terephthalic acid product to form a terephthalic acid cake with acetic acid;

(b) removing a substantial portion of a solvent in a water wash zone from the terephthalic acid cake with acetic acid to form a water-wet terephthalic acid cake; and

(c) routing the water-wet terephthalic acid cake to a vapor seal  
5 zone; and

(d) adding at least one diol to the water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to form the terephthalic acid/diol mixture.

In another embodiment of this invention, a process for producing a  
10 terephthalic acid/diol mixture is provided, the process comprises:

(a) removing a solvent from a slurry or cake terephthalic acid product in a solvent liquor exchange zone; wherein a substantial portion of the solvent in the slurry or cake terephthalic acid product is replaced with water to form a water-wet terephthalic acid cake;

15 (b) routing the water-wet terephthalic acid cake to a vapor seal zone; and

(c) adding at least one diol to the water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to form the terephthalic acid/diol mixture.

20 In another embodiment of this invention, a process for producing a terephthalic acid/diol mixture is provided, the process comprises:

(a) removing in a solvent wash zone impurities from a slurry or cake terephthalic acid product from a terephthalic acid cake with acetic

acid; wherein the solvent wash zone comprises at least one solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C ;

5 (b) removing a substantial portion of a solvent in a water wash zone from the terephthalic acid cake with acetic acid to form a water-wet terephthalic acid cake; wherein the water wash zone comprises at least one solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C;

10 (c) adding at least one diol to the water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to form the terephthalic acid/diol mixture; wherein the adding occurs at a temperature between about 40 °C to about 290 °C; wherein the diol is ethylene glycol.

15 In another embodiment of this invention, a process for producing a carboxylic acid/diol mixture is provided, the process comprises:

(a) removing in a solid-liquid separation zone impurities from a carboxylic acid slurry to form a slurry or cake carboxylic acid product and a mother liquor stream;

20 (b) adding solvent to a slurry or cake carboxylic acid product in a solvent wash zone to the slurry or cake carboxylic acid product to produce a carboxylic acid cake with solvent and a solvent mother liquor stream;

(c) adding water in a water wash zone to the carboxylic cake with solvent to produce a water-wet carboxylic acid cake and a solvent/water by product liquor stream;

(d) routing the water-wet carboxylic acid cake to a vapor seal  
5 zone; and

(e) adding at least one diol to the water-wet carboxylic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to form the carboxylic acid/diol mixture.

In another embodiment of this invention, a process for producing a  
10 terephthalic acid/diol mixture is provided, the process comprises:

(a) removing in a solid-liquid separation zone impurities from a crude terephthalic acid slurry to form a slurry or cake terephthalic acid product and a mother liquor stream;

(b) adding solvent in a solvent wash zone to the slurry or cake  
15 terephthalic acid product to produce a terephthalic acid cake with solvent and a solvent mother liquor stream;

(c) adding water in a water wash zone to the terephthalic acid cake with solvent to produce a water-wet terephthalic acid cake and a solvent/water by product liquor stream;

(d) routing the water-wet terephthalic acid cake to a vapor seal  
20 zone; and

(e) adding at least one diol to the water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to remove a portion of the water to form the terephthalic acid/diol mixture.

These objects, and other objects, will become more apparent to  
5 others with ordinary skill in the art after reading this disclosure.

#### **BRIEF DESCRIPTION OF THE DRAWINGS**

Figure 1 illustrates one embodiment of this invention, a process for  
10 producing a carboxylic acid/diol mixture.

Figure 2 illustrates another embodiment of this invention, a process for producing a carboxylic acid/diol mixture by utilizing a liquor exchange zone.

Figure 3 illustrates another embodiment of this invention, a process  
15 for producing a carboxylic acid/diol mixture by utilizing a solvent-water liquor exchange zone.

Figure 4 illustrates another embodiment of this invention, a process for producing a carboxylic acid/diol mixture by utilizing a solvent liquor exchange zone.

20

#### **DESCRIPTION OF THE INVENTION:**



In an embodiment of this invention shown in Figure 1, a process for producing a carboxylic acid/diol mixture **200** is provided. The process comprises:

Step (a) comprises optionally removing impurities from a carboxylic acid slurry **30** in a solid-liquid displacement zone **40** to form a slurry or cake carboxylic acid product **70** and a mother liquor stream **60**;

The carboxylic acid slurry comprises **30** at least one carboxylic acid, catalyst, at least one solvent, and impurities. The impurities typically comprise at least one or more of the following compounds: 4-carboxybenzaldehyde(4-CBA), trimellitic acid(TMA), and 2,6-dicarboxyfluorenone(2,6-DCF). Suitable solvents include, but are not limited to, aliphatic mono-carboxylic acids, preferably containing 2 to 6 carbon atoms, or benzoic acid and mixtures thereof and mixtures of these compounds with water. Preferably the solvent is acetic acid mixed with water, in a ratio of about 5:1 to about 99:1, preferably between about 8:1 and about 49:1. Throughout the specification acetic acid will be referred to as the solvent. However, it should be appreciated that other suitable solvents, such as those disclosed previously, may also be utilized. The solvent typically comprises acetic acid, but can be any solvent that has been previously mentioned.

The carboxylic acid slurry **30** can be produced by oxidizing in a oxidation zone an aromatic feed stock. In one embodiment, the aromatic feedstock comprises paraxylene. The oxidation zone comprises at least one

oxidation reactor, and the carboxylic acid slurry comprises at least one carboxylic acid. The oxidation reactor can be operated at temperatures between about 120°C and about 250°C, preferably about 140°C to about 170°C. Typically the aromatic feed stock comprises paraxylene and the  
5 carboxylic acid comprises terephthalic acid. In one embodiment of the invention the oxidation zone comprises a bubble column.

Therefore, for example, when terephthalic acid is utilized, the carboxylic acid slurry **30** would be referred to as terephthalic acid slurry and the carboxylic acid/diol mixture **200** would be referred to as a terephthalic  
10 acid/diol mixture.

Carboxylic acids include any carboxylic acid produced via controlled oxidation of an organic precursor compound. For example carboxylic acids include aromatic dicarboxylic acids preferably having 8 to 14 carbon atoms, aliphatic dicarboxylic acids preferably having 4 to 12 carbon atoms, or  
15 cycloaliphatic dicarboxylic acids preferably having 8 to 12 carbon atoms. Other examples of suitable carboxylic acids include, but are not limited to, terephthalic acid, benzoic, p-toulic, isophthalic acid, trimellitic acid, naphthalene dicarboxylic acid, cyclohexanedicarboxylic acid, cyclohexanediacetic acid, diphenyl-4,4'-dicarboxylic acid, diphenyl-3,4'-  
20 dicarboxylic acid, 2,2,-dimethyl-1,3-propandiol dicarboxylic acid, succinic acid, glutaric acid, adipic acid, azelaic acid, sebacic acid, and mixtures thereof.

Terephthalic acid slurry is conventionally synthesized via the liquid phase oxidation of paraxylene in the presence of suitable oxidation catalyst. Suitable catalysts include, but are not limited to, cobalt, manganese and bromine compounds, which are soluble in the selected solvent. In one  
5 embodiment of the invention the catalyst comprises cobalt, bromine and manganese. The cobalt and manganese combined can be in concentrations of about 100 ppm to about 2700 ppm by weight in the liquor. The bromine can be in concentrations of about 1000 ppm to about 2500 ppm by weight in the liquor.

10 The carboxylic acid slurry **30** is fed to a solid-liquid displacement zone **40** capable of removing a portion of the liquid contained in the carboxylic acid slurry **30** to produce a slurry or cake carboxylic acid product in conduit **70**. The removal of a portion of the liquid to produce a slurry or cake carboxylic acid product in conduit **70** can be accomplished by any  
15 means known in the art. A portion means at least 5% by weight of the liquid is removed. Typically, the solid-liquid displacement zone **40** comprises a solid-liquid separator that is selected from the group consisting of a decanter centrifuge, rotary disk centrifuge, belt filter, rotary vacuum filter, and the like. The carboxylic acid slurry in conduit **30** is fed to the solid-  
20 liquid displacement zone **40** comprising at least one solid-liquid separator. The solid-liquid separator(s) can be operated at temperatures between about 50°C to about 200°C, preferably 140°C to about 170°C. The solid-liquid separator(s) can be operated at pressures between about 0 psig to

about 200 psig. The solid-liquid separator in the solid-liquid displacement zone **40** may be operated in continuous or batch mode, although it will be appreciated that for commercial processes, the continuous mode is preferred.

5           The impurities are displaced from the solid-liquid displacement zone **40** into a mother liquor stream and withdrawn via line **60**. In one embodiment of the invention, additional solvent is fed to the solid-liquid displacement zone **40** via line **50** to reslurry the carboxylic acid slurry **30** and form a slurry or cake carboxylic acid product **70**. When a terephthalic  
10   acid slurry is utilized in the solid-liquid separation zone **40**, a slurry or cake terephthalic acid product is produced. The slurry or cake terephthalic acid product typically comprises terephthalic acid and acetic acid. The mother liquor **60** is withdrawn from solid-liquid displacement zone **40** via line **60** and comprises a solvent, typically acetic acid, catalyst, and bromine  
15   compounds. The mother liquor in line **60** may either be sent to a process for separating impurities from oxidation solvent via lines not shown or recycled to the catalyst system via lines not shown. One technique for impurity removal from the mother liquor **60** commonly used in the chemical processing industry is to draw out or "purge" some portion of the recycle  
20   stream. Typically, the purge stream is simply disposed of or, if economically justified, subjected to various treatments to remove undesired impurities while recovering valuable components. Examples of impurity removal

processes include U.S. Patent 4,939,297 and U.S. Patent 4,356,319, herein incorporated by reference.

Step (b) comprises removing in a solvent wash zone **80** residual impurities from a slurry or cake carboxylic acid product **70** to form a  
5 carboxylic acid cake with solvent **110** and a solvent mother liquor stream **100**.

Conduit **70** contains a slurry or cake carboxylic acid product **70** comprising a carboxylic acid, residual impurities and a solvent. The residual impurities comprise residual catalyst (typically but not limited to cobalt, manganese, or  
10 bromine). Suitable solvents include, but are not limited to, aliphatic mono-carboxylic acids, preferably containing 2 to 6 carbon atoms, or benzoic acid and mixtures thereof and mixtures of these compounds with water.

Preferably, the solvent is comprised of mainly acetic acid and/or some water. The ratio of acetic acid to water can range from 50:50 to 98:2 acetic  
15 acid to water by mass, more preferably in the range of 85:15 to 95:5, and most preferably in the range of 90:10 to 97:3. Suitable carboxylic acids include by are not limited to terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid, trimellitic acid, and mixtures thereof.

The slurry or cake carboxylic acid product **70** is in the range of 10-  
20 90% by weight carboxylic acid. Preferably the slurry or cake carboxylic acid product **70** is in the range of 25- 40% by weight carboxylic acid for a slurry and in the range of 70-90% by weight for the cake product. Most preferably, the slurry or cake carboxylic acid product **70** is in the range of

30-40% by weight carboxylic acid. The slurry or cake carboxylic acid product in conduit **70** is then introduced into a solvent wash zone **80**, wherein a substantial portion of solvent is recovered in the solvent mother liquor stream in conduit **100**. The solvent mother liquor **102** comprises a  
5 substantial portion of the solvent. In one embodiment of the invention, additional solvent can be added via conduit **90** counter current to the flow of the slurry or cake carboxylic acid product **70** in the solvent wash zone **80**. The amount of stages of solvent counter current wash can be any amount of stages necessary to produce the carboxylic cake with solvent to the  
10 desired purity. Typically, the amount of stages in the solvent counter current wash can be about 1 to about 8, preferably about 2 to about 6, most preferably about 2 to about 4. For wash with more than one stage, counter current flow is preferable. Solvent counter current wash is preferable because typically it results in less solvent being used as compared to a  
15 process when solvent counter current wash is not utilized.

The solvent wash zone **80** comprises at least one solid-liquid separation device capable of efficiently separating solids and liquids. The solid-liquid separation device can typically be comprised of, but not limited to, the following types of devices: centrifuges, cyclones, rotary drum filters,  
20 belt filters, press filters, etc. The solvent wash zone **80** comprises at least one solid-liquid separation device(s) **110** which can operate within a temperature range of from approximately 40°C to 155°C. Preferably the solid-liquid separation device(s) **110** can operate within a temperature

range of from about 80°C to about 150°C. Most preferably the solid-liquid separation device(s) **110** can operate within a temperature range of from about 90°C to about 150°C. A carboxylic acid cake with solvent **110**, is produced wherein the moisture composition of the carboxylic acid cake with solvent **110** can be in the range of 0.5-30% by weight moisture, preferably in the range of 1-20% moisture, most preferably in the range of 1-10% moisture. Optionally, the residual solvent can be removed by a gas displacement step to minimize solvent contamination with wash. When the carboxylic acid is terephthalic acid and the solvent is acetic acid a terephthalic acid cake with acetic acid is produced.

Step (c) comprises optionally removing a substantial portion of a solvent in a water wash zone **120** from the carboxylic acid cake with solvent **110** to form a water-wet carboxylic acid cake **100** and a solvent/water byproduct liquor stream **140**.

The carboxylic acid cake with solvent **110**, is then subjected to a wash or "rinsing" with water or substantially water with residual amounts of solvent in the water wash zone **120**, wherein a substantial portion of the solvent is replaced with water to form a water-wet carboxylic acid cake **150**. The water-wet carboxylic acid cake **150**, is preferably in the range of about 0.5% to about 30% moisture, more preferably in the range of about 1 to about 20% moisture, and most preferably in the range of about 1% to about 10% moisture. The residual moisture of the water-wet carboxylic acid cake **150**, should contain less than about 2% solvent on a mass basis.

Additionally, the water-wet carboxylic acid cake **150** should contain less than 1% of any metals, preferably less than 100 ppm by weight, most preferably less than 10 ppm by weight, typically used as catalysts in p-xylene oxidation, in the slurry or cake carboxylic acid product in conduit **70**,  
5 should remain in the water-wet carboxylic acid cake **150**. Examples of metals include but are not limited to cobalt, and manganese.

Wash water is introduced into the water wash zone **120** via conduit **130**. The wash water should be, on a continuous basis, comprise a mass feed rate in ratio with the solids in the carboxylic cake with solvent **110** in  
10 the range of about 0.1:1 to about 1.5:1, preferably in the range of about 0.1:1 to about 0.6:1, most preferably in the range of about 0.2:1 to about 0.4:1. There are no limitations on the temperature or pressure of the wash water including the use of vaporized water, steam, or a combination of water and steam, as wash. In one embodiment of the invention, wash  
15 water is introduced counter current to the carboxylic acid cake with solvent.

Additional wash water can be added via conduit **130** counter current to the flow of the carboxylic acid cake with solvent **110** in the water wash zone **120**. The amount of stages of water counter current wash can be any amount of stages necessary to produce the water wet carboxylic acid cake  
20 to the desired purity. Typically, the amount of stages in the water counter current wash can be about 1 to about 8, preferably about 2 to about 6, most preferably about 2 to about 4. For wash with more than one stage, counter current flow is preferable. Water counter current wash is preferable



because typically it results in less water being used as compared to a process when water counter current wash is not utilized.

The water wash zone comprises a solid-liquid separation device **120** can typically be comprised of, but not limited to, the following types of devices: centrifuges, cyclones, rotary drum filters, belt filters, press filters, etc. The solid-liquid separation device can be operated within a temperature range of from about 40°C to about 155°C. Preferably, the second solid-liquid separation device can operate within a temperature range of from about 80°C to about 150°C. Most preferably, the second solid-liquid separation device can operate within a temperature range of from about 90°C to about 150°C

Optionally, the solvent/water byproduct liquor from the water wash zone **120**, is segregated from the solvent mother liquor stream produce by the solvent wash zone **80**.

Step (d) comprises routing the water-wet carboxylic acid cake **150** to a vapor seal zone **160**.

The water-wet carboxylic acid cake **150** is passed through a vapor seal zone **160** comprising a vapor seal device, and exits the vapor seal device via conduit **170**. The vapor seal device allows the water-wet carboxylic acid cake **150** to exit the counter current wash zone **120** but prevents diol from the carboxylic acid/diol mixing zone **180** from entering the counter current wash zone or any process zone proceeding the vapor seal zone **160**. The vapor seal device can be any device known in the art.

Examples include, but are not limited to rotary air lock valve, and solid conveying extruders.

Step (e) comprises adding at least one diol **190** to the water-wet carboxylic acid cake **170** in a carboxylic acid/diol mixing zone **180** to  
5 remove a portion from the water-wet carboxylic acid cake **170** of the water to form the carboxylic acid/diol mixture **200**.

Finally, the water-wet carboxylic acid cake **170**, which is now substantially free of solvent is combined with a diol **190** in a carboxylic acid mixing zone **180**, to form a carboxylic acid/diol mixture **200** suitable for PET  
10 production and other polyesters or co-polyesters. There are no special limitations on the carboxylic acid/diol mixing zone **180** with the exception that it comprises a device that must provide intimate contact between the water-wet carboxylic acid cake **170**, and the diol **190** to produce a the carboxylic acid/diol mixture **200**. Examples of such devices include, but  
15 are not limited to the following: an agitated vessel, static mixer, screw conveyor, PET esterification reactor(s), etc. A solid eductor could be used to introduce the water-wet carboxylic acid cake into the device. Nor is there any specific limitation on the temperature range at which the device can operate. However, it is preferable that the temperature of device does not  
20 exceed approximately 280°C, temperatures normally found within PET esterification reactors.

At least one diol in conduit **190** can be introduced in such a manner as to optionally displace the water as the dominant slurrying liquid. This

can be accomplished by introducing a diol via conduit **190** as a saturated liquid at a temperature which is sufficient to vaporize the water. In one embodiment of the invention, the diol in conduit **190** is introduced as a saturated or superheated vapor. The diol in conduit **190** is at least one  
5 selected from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanedimethanol, and mixtures thereof. Preferably, the diol in conduit **190** is ethylene glycol. Note that within the system shown in figure 1, a substantially dry carboxylic acid solid is not formed. The primary  
10 advantage in not forming a carboxylic acid dry solid is the elimination of solids handling equipment. Examples of solids handling equipment include but are not limited to a dryer, convey systems, and silos.

In other embodiments of this invention step (a), step (b) and step (c) can be combined into one zone known as the liquor exchange zone **250** as  
15 shown in figure 2. The liquor exchange zone **250** comprises at least one solid-liquid separation device capable of performing the combined function of the solid-liquid separation zone **40**, the solvent wash zone **80** and the water wash zone **120** as previously described. Step (b) and step (c) can also be combined into one zone known as the solvent-water liquor  
20 exchange zone **260** as shown in Figure 3. Finally step (a) and step (b) can be combined into one zone known as the solvent liquor exchange zone **270** as show in Figure 4. In each of the above embodiments comprises at least one solid-liquid separation device capable of performing the functions of the

combined zones as previously described. Examples of devices that can be used in the liquor exchange zone **250**, or the solvent-water liquor exchange zone **260**, or the solvent liquor exchange zone **270** included but are not limited to, the following type of devices centrifuges, cyclones, filters, and  
5 such or combination thereof.

**WE CLAIM:**

1. A process for producing a carboxylic acid/diol mixture, said process comprising:

(a) removing in a liquor exchange zone impurities from a  
5 carboxylic acid slurry to form a water-wet carboxylic acid cake, a mother liquor stream, a solvent mother liquor stream, and a solvent/water byproduct liquor stream;

(b) routing said water-wet carboxylic acid cake to a vapor seal zone; and

10 (c) adding at least one diol to said water-wet carboxylic acid cake in a carboxylic acid/diol mixing zone to form said carboxylic acid/diol mixture.

2. A process according to claim 1 wherein said carboxylic acid is selected from a group consisting of terephthalic acid, isophthalic acid,  
15 naphthalene dicarboxylic acid, trimellitic acid, and mixtures thereof.

3. A process according to claim 1 or 2 wherein said diol is selected from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanedimethanol, and mixtures thereof.

20 4. A process according to claim 1 wherein said carboxylic acid/diol mixing zone comprises at least one device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification reactor.

5. A process according to claim 1 wherein said carboxylic acid is terephthalic acid and said diol is ethylene glycol.

6. A process for producing a carboxylic acid/diol mixture, said process comprising:

5 (a) removing in a solvent liquor exchange zone impurities from a carboxylic acid slurry to form a carboxylic acid cake with solvent, a mother liquor stream, and a solvent mother liquor stream;

(b) adding water in a water wash zone to said carboxylic cake with solvent to produce a water-wet carboxylic acid cake and a  
10 solvent/water by product liquor stream;

(c) routing said water-wet carboxylic acid cake to a vapor seal zone; and

(d) adding at least one diol to said water-wet carboxylic acid cake in a carboxylic acid/diol mixing zone to form said carboxylic acid/diol  
15 mixture.

7. A process according to claim 6 wherein said carboxylic acid is selected from a group consisting of terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid, trimellitic acid and mixtures thereof.

8. A process according to claim 6 or 7 wherein said diol is selected  
20 from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanedimethanol, and mixtures thereof.

9. A process according to claim 6 wherein said carboxylic acid/diol mixing zone comprises at least one device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification reactor.

5 10. A process according to claim 6 wherein said carboxylic acid is terephthalic acid and said diol is ethylene glycol.

11. A process for producing a carboxylic acid/diol mixture, said process comprising:

(a) removing in a solid-liquid separation zone impurities from a  
10 carboxylic acid slurry to form a slurry or cake carboxylic acid product and a mother liquor stream;

(b) removing in a solvent-water liquor exchange zone residual impurities from said slurry or cake carboxylic acid product to form a water-wet carboxylic acid cake, a solvent mother liquor stream, and a  
15 solvent/water byproduct liquor stream;

(c) routing said water-wet carboxylic acid cake to a vapor seal zone; and

(d) adding at least one diol to said water-wet carboxylic acid cake in a carboxylic acid/diol mixing zone to form said carboxylic acid/diol  
20 mixture.

12. A process according to claim 11 wherein said carboxylic acid is selected from a group consisting of terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid, trimellitic acid and mixtures thereof.

13. A process according to claim 11 or 12 wherein said diol is selected from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanedimethanol, and mixtures thereof.

5 14. A process according to claim 11 wherein said carboxylic acid/diol mixing zone comprises at least one device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification reactor.

15 15. A process according to claim 11 wherein said carboxylic acid is terephthalic acid and said diol is ethylene glycol.

16. A process for producing a carboxylic acid/diol mixture, said process comprising the following steps:

(a) removing a solvent from a slurry or cake carboxylic acid product in a solvent-water liquor exchange zone; wherein a substantial  
15 portion of the solvent in said slurry or cake carboxylic acid product is replaced with water to form a water-wet carboxylic acid cake;

(b) routing said water-wet carboxylic acid cake to a vapor seal zone; and

(c) adding at least one diol to said water-wet carboxylic acid cake  
20 in a carboxylic acid/diol mixing zone to form said carboxylic acid/diol mixture.



17. A process according to claim 16 wherein said carboxylic acid is selected from a group consisting of terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid, trimellitic and mixtures thereof.

18. A process according to claim 16 or 17 wherein said diol is selected  
5 from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanedimethanol, and mixtures thereof.

19. A process according to claim 16 wherein said carboxylic acid/diol  
10 mixing zone comprises at least one device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification reactor.

20. A process for producing a terephthalic acid/diol mixture, said process comprising:

(a) removing in a solvent wash zone residual impurities from a  
15 slurry or cake terephthalic acid product to form a terephthalic acid cake with acetic acid;

(b) removing a substantial portion of a solvent in a water wash zone from said terephthalic acid cake with acetic acid to form a water-wet terephthalic acid cake; and

20 (c) routing said water-wet terephthalic acid cake to a vapor seal zone; and

(d) adding at least one diol to said water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to form said terephthalic acid/diol mixture.

21. A process according to claim 20 wherein said solvent wash zone  
5 comprises a solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C.

22. A process according to claim 21 wherein said water wash zone comprises a solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C.

10 23. A process according to claim 20 or 21 wherein said adding occurs at a temperature between about 40 °C to about 290 °C.

24. A process according to claim 20 wherein said diol is selected from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol,  
15 cyclohexanedimethanol, and mixtures thereof.

25. A process according to claim 20 wherein said diol is ethylene glycol.

26. A process according to claim 20 wherein said carboxylic acid/diol mixing zone comprises a device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification  
20 reactor.

27. A process for producing a terephthalic acid/diol mixture, said process comprising:

(a) removing a solvent from a slurry or cake terephthalic acid product in a solvent-water liquor exchange zone; wherein a substantial portion of the solvent in said slurry or cake terephthalic acid product is replaced with water to form a water-wet terephthalic acid cake;

5 (b) routing said water-wet terephthalic acid cake to a vapor seal zone; and

(c) adding at least one diol to said water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to form said terephthalic acid/diol mixture.

10 28. A process according to claim 27 wherein said solvent liquor exchange zone comprises a solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C.

29. A process according to claim 27 wherein said adding occurs at a temperature between about 40 °C and 290 °C.

15 30. A process according to claim 27 wherein said diol is selected from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanediol, and mixtures thereof.

31. A process according to claim 27 wherein said diol is ethylene glycol.

20 32. A process according to claim 27 wherein said carboxylic acid/diol mixing zone comprises a device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification reactor.

33. A process for producing a terephthalic acid/diol mixture, said process comprising:

(a) removing in a solvent wash zone residual impurities from a slurry or cake terephthalic acid product from a terephthalic acid cake with  
5 acetic acid; wherein said solvent wash zone comprises at least one solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C ;

(b) removing a substantial portion of a solvent in a water wash zone from said terephthalic acid cake with acetic acid to form a water-wet  
10 terephthalic acid cake; wherein said water wash zone comprises at least one solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C;

(c) routing said water-wet terephthalic acid cake to a vapor seal zone; and

15 (d) adding at least one diol to said water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to form said terephthalic acid/diol mixture; wherein said adding occurs at a temperature between about 40 °C to about 290 °C; wherein said diol is ethylene glycol.

34. A process for producing a carboxylic acid/diol mixture, said process  
20 comprising:

(a) removing in a solid-liquid separation zone impurities from a carboxylic acid slurry to form a slurry or cake carboxylic acid product and a mother liquor stream;

(b) adding solvent to a slurry or cake carboxylic acid product in a solvent wash zone to said slurry or cake carboxylic acid product to produce a carboxylic acid cake with solvent and a solvent mother liquor stream;

(c) optionally, adding water in a water wash zone to said  
5 carboxylic cake with solvent to produce a water-wet carboxylic acid cake and a solvent/water by product liquor stream;

(d) routing said water-wet carboxylic acid cake or said carboxylic acid cake with solvent to a vapor seal zone; and

(e) adding at least one diol to said water-wet carboxylic acid cake  
10 in a carboxylic acid/diol mixing zone to form said carboxylic acid/diol mixture.

35. A process according to claim 34 wherein said carboxylic acid is selected from a group consisting of terephthalic acid, isophthalic acid, naphthalene dicarboxylic acid, trimellitic acid and mixtures thereof.

15 36. A process according to claim 34 or 35 wherein said diol is selected from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanedimethanol, and mixtures thereof.

37. A process according to claim 34 wherein said carboxylic acid/diol  
20 mixing zone comprises at least one device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification reactor.

38. A process according to claim 34 wherein said carboxylic acid is terephthalic acid and said diol is ethylene glycol.

39. A process for producing a terephthalic acid/diol mixture, said process comprising:

5 (a) removing in a solid-liquid separation zone impurities from a terephthalic acid slurry to form a slurry or cake terephthalic acid product and a mother liquor stream;

(b) adding solvent in a solvent wash zone to said slurry or cake terephthalic acid product to produce a terephthalic acid cake with solvent  
10 and a solvent mother liquor stream;

(c) optionally, adding water in a water wash zone to said terephthalic acid cake with solvent to produce a water-wet terephthalic acid cake and a solvent/water by product liquor stream;

(d) routing said water-wet terephthalic acid cake or said  
15 carboxylic acid cake with solvent to a vapor seal zone; and

(e) adding at least one diol to said water-wet terephthalic acid cake in a carboxylic acid/diol mixing zone to form said terephthalic acid/diol mixture.

40. A process according to claim 39 wherein said solvent wash zone  
20 comprises a solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C.

41. A process according to claim 40 wherein said water wash zone comprises a solid-liquid separation device that is operated at a temperature between about 40 °C to about 155 °C.
42. A process according to claim 39 or 40 wherein said adding occurs at  
5 a temperature between about 40 °C and about 290 °C.
43. A process according to claim 39 wherein said diol is selected from the group consisting of ethylene glycol, diethylene glycol, n-butylene glycol, i-butylene glycol, n-propylene glycol, 1,4 butanediol, cyclohexanedimethanol, and mixtures thereof.
- 10 44. A process according to claim 39 wherein said diol is ethylene glycol.
45. A process according to claim 39 wherein said carboxylic acid/diol mixing zone comprises a device selected from the group consisting of an agitated vessel, a static mixer, a screw conveyor, and a PET esterification reactor.
- 15 46. A process according to claim 34 or 39 wherein said solvent is added counter current to the flow of said slurry or cake carboxylic acid product.
47. A process according to claim 34 or 39 wherein said water is added counter current to the flow of said carboxylic acid cake with solvent.
48. A process according to claim 46 wherein said water is added counter  
20 current to the flow of said carboxylic acid cake with solvent.
49. A process according to claim 48 wherein said water wash zone comprises from about 2 to about 4 stages of water counter current washes.

50. . . A process according to claim 46 wherein said solvent wash zone comprises from about 2 to about 4 stages of solvent counter current washes.


51. . . A process according to claim 47 wherein said water wash zone  
5 comprises from about 2 to about 4 stages of water counter current washes.



**ABSTRACT OF THE INVENTION:**

The present invention relates to a process by which a carboxylic acid/diol mixture is obtained from a slurry or cake carboxylic acid product  
5 without isolation of a substantially dry carboxylic acid solid. More specifically, the present invention relates to a process by which a terephthalic acid/ethylene glycol mixture suitable as a starting material for polyester or co-polyester production is obtained from a slurry or cake  
10 terephthalic acid product without isolation of a substantially dry terephthalic acid solid.

Fig. 1



1/2

Fig. 2






Fig. 3



2/2

Fig. 4



Please type a plus (+) sign in this box → ☐

PTO/SB/02A (11-00)

Approved for use through 10/31/2002. OMB 0651-0032

U.S. Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

<b>DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION</b> <b>(37 CFR 1.63)</b>  <input checked="" type="checkbox"/> Declaration Submitted with Initial Filing <input type="checkbox"/> Declaration Submitted after Initial Filing (surcharge (37 CFR 1.16 (e)) required)	Attorney Docket Number	80002/US01
	First Named Inventor	Parker et al.
	<b>COMPLETE IF KNOWN</b>	
	Application Number	
	Filing Date	
	Group Art Unit	
	Examiner Name	

As a below named inventor, I hereby declare that:

My residence, mailing address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**PROCESS FOR PRODUCTION OF A CARBOXYLIC ACID/DIOL MIXTURE SUITABLE FOR USE IN POLYESTER PRODUCTION**

(Title of Invention)

the specification of which

☒ is attached hereto

OR

☐ was filed on (MM/DD/YYYY)

as United States Application Number or PCT International

Application Number and was amended on (MM/DD/YYYY) (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56, including for continuation-in-part applications, material information which became available between the filing date of the prior application and the national or PCT international filing date of the continuation-in-part application.

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached? Yes	No
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

I hereby claim the benefit under Title 35 USC 119(e) of any United States provisional application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)

☐ Additional Provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

[Page 1 of 1]

Burden Hour Statement: This form is estimated to take 21 minutes to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Department of Commerce P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

Please type a plus (+) sign in this box → ☐

PTO/SB/02A (11-00)

Approved for use through 10/31/2002. OMB 0651-0032

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

## DECLARATION — Utility or Design Patent Application

I hereby claim the benefit under 35 USC 120 of any United States application(s), or 365(c) of any PCT International application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 USC 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations § 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application Number	PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (If applicable)

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority data sheet attached hereto.

As a named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

Name	Registration Number	Name	Registration Number
Michael J. Blake	37,096	Eric D. Middlemas	53,325
Betty J. Boshears	33,864	Polly C. Owen	44,991
Dennis V. Carmen	35,007	Steven A. Owen	50,355
Michael K. Carrier	42,391	Jonathan D. Wood	39,076
Bernard J. Graves, Jr.	33,239		

☐ Additional registered practitioner(s) named on supplemental Registered Practitioner Information sheet attached hereto

Direct all correspondence to:

Name	Steven A. Owen		
Address	Eastman Chemical Company		
Address	P.O. Box 511		
City	Kingsport	State	Tennessee
Country	USA	Telephone	(423) 229-5534
		Fax	(423) 229-1239

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor ☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))	Family Name or Surname
Kenny Randolph	Parker

Inventor's Signature

*Kenny R. Parker*

Date *Jun 15, 2004*

Residence: City	State	Country	Citizenship
Afton	Tennessee	U.S.A.	U.S.A.

Mailing Address

599 Tyne Gray Road

City	State	ZIP	Country
Afton	Tennessee	376164409	U.S.A.

☒ Additional inventors are being named on the 1 supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto.

[Page 2 of 2]

Burden Hour Statement: This form is estimated to take 21 minutes to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Department of Commerce P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

Please type a plus (+) sign in this box ☐ +

PTO/SB/02A (11-00)

Approved for use through 10/31/2002. OMB 0651-0032  
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

DECLARATION		ADDITIONAL INVENTOR(S) Supplemental Sheet	
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any))	Family Name or Surname		
Robert	Lin		
Inventor's Signature <u>Robert Lin</u>		Date <u>January 14, 2004</u>	
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Mailing Address 4533 Palomino Drive			
City Kingsport	State Tennessee	ZIP 37664	Country U.S.A.
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any))	Family Name or Surname		
Philip Edward	Gibson		
Inventor's Signature <u>Philip Edward Gibson</u>		Date <u>January 14, 2004</u>	
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Mailing Address 2244 Charsley Road			
City Kingsport	State Tennessee	ZIP 37660	Country U.S.A.
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle (if any))	Family Name or Surname		
Inventor's Signature		Date	
Residence: City	State	Country	Citizenship
Mailing Address			
City	State	ZIP	Country

[Page 3 of 3]

Burden Hour Statement: This form is estimated to take 21 minutes to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Department of Commerce P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.